

PRODUCT DATASHEET



Bisalloy Steels Pty Ltd
18 Resolution Drive, Unanderra
PO Box 1246 Unanderra
NSW 2526 Australia

P: (02) 4272 0444
F: (02) 4272 0456
E: technical@bisalloy.com.au
www.bisalloy.com.au

BISALLOY® Wear 550 Steel

BISALLOY® Wear 550 steel is a through-hardened, abrasion-resistant steel plate. While being a wear plate, BISALLOY® Wear 550 steel offers the optimum combination of hardness, impact resistance and formability for wear applications requiring extensive forming/drilling or fabrication in abrasive applications.

Application

With a nominal hardness of 550 HBW, BISALLOY® Wear 550 steel is an ideal choice for applications that require a balance of hardness and toughness, including:

- Deflector plates
- Demolition tools
- Rippers and lifting tyres
- Chutes
- Storage bins
- Dump truck liners
- Civil and earthmoving bucket

Mechanical Properties

Properties	Specification	Typical
0.2% Proof Stress	-	1,400 MPa
Tensile Strength	-	1850 MPa
Elongation in 50mm G.L.	-	8%
Charpy Impact (Longitudinal) -40°C (10MM x 10mm)	-	10J
Hardness	530-570 HB	550 HB

Chemical Composition

Thickness (mm)	Weight %	C	P	Mn	Si	S	Ni	Cr	Mo	B	CE(IIW)*	CET*
8 – 50	Maximum	0.38	0.020	0.50	0.35	0.005	1.00	1.20	0.30	0.002	0.68*	0.46*

*Typical average

PLEASE NOTE: PLEASE NOTE: Every care has been taken to ensure the accuracy of information contained in this manual which supersedes earlier publications, however Bisalloy Steels shall not be liable for any loss or damage whatsoever caused from the application of such information. Typical values are provided for reference information only and no guarantee is given that a specific plate will provide these properties. Information is subject to change without notice. **Published June 2023**