

BISALLOY® ARMOUR HTA400 STEEL

Introduction

BISALLOY® ARMOUR HTA400 steel (High Toughness Armour) - a quenched and tempered steel armour plate, possessing very good weldability, suitable for use in both military and civil applications where high rates of shock loading and resistance to penetration by ballistic projectiles are required.

Brinell hardness

Thickness (mm)	Specification	Typical
5 - 50 ¹	370-430 HB	400 HB

Tensile properties

Property	Typical
0.2% Proof Stress	1080 MPa
Tensile Strength	1250 MPa
Elongation in 50 mm GL	14%

Charpy impact values

Thickness (mm)	Test Piece	Test Temp	Min. Energy (Transverse)	Min. Energy (Longitudinal)
5	10 x Thk	-40°C	By Agreement	By Agreement
6 - <8	10 x 5	-40°C	9J	9J
8 - <12	10 x 7.5	-40°C	13J	13J
≥12	10 x 10	-40°C	17J	17J

Chemistry

Product chemical analyses are taken on a per-heat basis. Chemical analysis is as follows:

Chemical composition

Thickness (mm)	Weight %	C	P	Mn	Si	S	Ni	Cr	Mo	B	CE(IIW)	CET
5 - 50 ¹	Maximum	0.32	0.025	1.50	0.60	0.005	0.50	1.20	0.30	0.002	0.61*	0.40*

Thickness tolerance

Thickness (mm)	Special Tolerance
5 - 25	-0.0 + 1.0
>25 - 50	-0.0 + 1.2

Test frequency

Per Plate	Per Batch	By Agreement
Hardness	Charpy (L), Charpy (T)	Thickness, Tensile, Ballistic Properties, Product Analysis

PRODUCT DATA SHEET



BISALLOY® ARMOUR HTA400 STEEL

Other

Equivalent Specification	Surface Finish
NIL	Shotblasted

Fabrication

For advice on fabrication refer to relevant Bisalloy technical brochures.
Contact Bisalloy direct or visit www.bisalloy.com.au

* Typical for 12mm plate

¹ Other thicknesses may be available on application

PLEASE NOTE: Every care has been taken to ensure the accuracy of information contained in this manual which supersedes earlier publications, however Bisalloy Steels shall not be liable for any loss or damage whatsoever caused from the application of such information. Typical values are provided for reference information only and no guarantee is given that a specific plate will provide these properties. Information is subject to change without notice. **Published August 2020**



1300 BISALLOY | www.bisalloy.com.au

BIS0421 - BISALLOY® ARMOUR HTA400 STEEL - AUGUST 2020

BISALLOY is a registered trade mark of Bisalloy Steels Group Limited, ABN 22 098 674 545